

Douglas Fir.

| *Pseudotsuga menziesii* |



All images used are for representation purposes only.



Douglas Fir.

A versatile softwood with moderate durability, making it suitable for both internal and external joinery. We stock old growth, slow-grown timber from the West Coastal region of Canada in the best available grade -No.2 clear & better, which gives the best results in service. Douglas Fir is sometimes called Oregon Pine but this is not a name recognised in the USA or Canada.

For more information please visit: www.sykestimber.co.uk

Origin:
Western Canada.

Density:
530kgs/m³

Availability:
Slow grown Square edged kiln dried boards.

Movement in Service:
Small.

Grade:
No.2 Clear and Better.

Thicknesses available:
1", 1.5", 2", 2.5", 3", 4", 6"

Colour:
Reddish brown heartwood, paler sapwood.

Length and width specification:
6' and longer x 4" and wider

Applications:
Joinery such as doors and windows, boat work.

Basic price Level:
Medium.

Durability:
Moderately durable.

Summary:
A versatile softwood for external or internal joinery and boat work, especially masts and spars. Vertical grain is ideal for door stock.