

# Ash, European White.

| **Fraxinus excelsior** |



All images used are for representation purposes only.



## Ash, European White.

A very clean and clear production, pale creamy white in colour, with a coarse even texture. European Ash is noted for its toughness and flexibility, so is a traditional wood for coachbuilding, tool handles, and sporting goods such as tennis rackets and cricket stumps, especially when air seasoned. Kilned stocks are also suitable for internal joinery and furniture. Ash is also a very good bending wood and much used for 'Windsor' bent-wood chair backs.

For more information please visit: [www.sykestimber.co.uk](http://www.sykestimber.co.uk)

<b>Origin.</b> Europe and UK.	<b>Density.</b> 650-700kgs/m <sup>3</sup>
<b>Availability.</b> Waney Edged Air Dried and Kiln Dried boards.	<b>Movement in Service.</b> Medium
<b>Grade.</b> Sykes grade.	<b>Thicknesses available.</b> 27mm, 41mm, 52mm, 80mm
<b>Colour.</b> Creamy white with pronounced growth rings	<b>Length and width specification.</b> 1.8m and longer x 200mm and wider.
<b>Applications.</b> Coachbuilding, Furniture, Joinery, Woodware.	<b>Basic price Level.</b> Medium.
<b>Durability.</b> Non-durable.	<b>Summary.</b> A tough and elastic timber with good bending and turning properties. Air dried timber is the most flexible for coach-building work. Suitable also for internal furniture, joiner and woodware.